

# 3M Scotch-Weld™ Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp  
2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

Technical Data

October 2018

## Product Description

- One part 250°F (121°C) curing 100% solids, 3M™ Scotch-Weld™ Epoxy Adhesive 2214 is a paste consistency epoxy adhesive designed for bonding metals and many high temperature plastics such as fiberglass reinforced plastic, polyester, and phenolics.
- 3M™ Scotch-Weld™ Adhesive 2214 Regular is an aluminum filled general purpose product for use in applications where high strength bonds are needed in a temperature range of -67°F to 250°F (-53°C to 121°C).
- 3M™ Scotch-Weld™ Adhesive 2214 Hi-Dense is a deaerated version of Scotch-Weld adhesive 2214 regular for use where a very dense, void free bondline is required.
- 3M™ Scotch-Weld™ Adhesive 2214 Hi-Temp and Hi-Temp New Formula are aluminum filled, deaerated products for use where higher strengths are required between 180°F to 350°F (82°C to 177°C).
- 3M™ Scotch-Weld™ Adhesive 2214 Non-Metallic Filled is a non-metal filled version of Scotch-Weld adhesive 2214 regular.

## Typical Uncured Physical Properties

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

	3M™ Scotch-Weld™ Epoxy Adhesive 2214				
	Regular	Hi-Dense	Hi-Temp	Hi-Temp New Formula	Non-Metallic Filled
Viscosity (Approx.) time to deliver 20 grams @ 50 psi thru a .104" orifice (seconds)	60-200	60-200	15-30	100-250	50-200
Viscosity (Brookfield)	Because of Thixotropic paste nature of these products Brookfield viscosity will be over 1,000,000 cps.				
Color	Gray	Gray	Gray	Gray	Cream
Base	Modified Epoxy	Modified Epoxy	Modified Epoxy	Modified Epoxy	Modified Epoxy
Net Weight (lbs/gal)	12.0	12.6	12.0	13.8	9.6

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

### Typical Cured Physical Properties

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

	3M™ Scotch-Weld™ Epoxy Adhesive 2214				
	Regular	Hi-Dense	Hi-Temp	Hi-Temp New Formula	Non-Metallic Filled
Color	Gray	Gray	Gray	Gray Brown	Cream to Tan
Shore D Hardness (Approx.)	85	85	88	85	85
Elongation (Approx. %)	<2	<2	1	1	<2
Ultimate Tensile (Approx. psi)	10,000	10,000	8,000	–	9,000
Modulus Elasticity (Approx. psi)	750,000	750,000	800,000	–	700,000

### Typical Thermal Properties (Cured)

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

	Thermal Conductivity (BTU/HR/FT <sup>2</sup> /°F/FT)	Coefficient of Thermal Expanse (in./in./°C)
3M™ Scotch-Weld™ Adhesive 2214 Regular	.231	49 x 10 <sup>-6</sup> (between 0-80°C)
3M™ Scotch-Weld™ Adhesive 2214 Hi-Dense	.231	49 x 10 <sup>-6</sup> (between 0-80°C)
3M™ Scotch-Weld™ Adhesive 2214 Hi-Temp	.189	48 x 10 <sup>-6</sup> (between 0-80°C)
3M™ Scotch-Weld™ Adhesive 2214 Hi-Temp New Formula	.244	44 x 10 <sup>-6</sup> (between -60 - +80°C)
3M™ Scotch-Weld™ Adhesive 2214 Non-Metallic Filled	.121	130 x 10 <sup>-6</sup> (between -30 - 100°C)

### Typical Electrical Properties (Cured)

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

Dielectric Constant (1) **ASTM-D-150**

Dissipation Factor (2) **ASTM-D-150**

Power Range 1.00 KC Test Temperature		73°F (23°C)	140°F (60°C)	194°F (90°C)	219°F (104°C)
Scotch-Weld adhesive 2214 Regular	(1) (2)	10.5 0.126	11.1 0.463	16.7 0.346	24.0 0.515
Scotch-Weld adhesive 2214 Hi-Dense	(1) (2)	10.5 0.126	11.1 0.463	16.7 0.346	24.0 0.515
Scotch-Weld adhesive 2214 Hi-Temp	(1) (2)	6.2 0.021	7.6 0.023	7.8 0.025	8.0 0.025
Scotch-Weld adhesive 2214 Non-Metallic Filled	(1) (2)	4.61 0.0135	4.96 0.0148	– –	– –
Scotch-Weld adhesive 2214 Hi-Temp New Formula	(1) (2)	– –	– –	– –	– –

# 3M™ Scotch-Weld™

Arc Resistance      ASTM-D-495-61  
Dielectric Strength      ASTM-D-149

## Epoxy Adhesives

Surface Resistivity      ASTM-D-257  
Volume Resistivity      ASTM-D-257

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

### Typical Electrical Properties (Cured) [continued]

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

3M™ Scotch-Weld™ Epoxy Adhesive 2214	ARC Resistance (Seconds)	Dielectric Strength (Volts Per Mil Thickness)		Surface Resistivity (500 Volts-DC)	Volume Resistivity (500 Volts-DC)
		Volts/Mil	Sample Thickness Inches	Ohms/Square 73°F (23°C)	Ohms-CM 73°F (23°C)
Regular	76	77	0.0366	$9.8 \times 10^{12}$	$2.8 \times 10^{13}$
Hi-Dense	76	77	0.0366	$9.8 \times 10^{12}$	$2.8 \times 10^{13}$
Hi-Temp	119	347	0.038	$1.1 \times 10^{17}$	$9.4 \times 10^{14}$
Non-Metallic Filled	26	570	0.039	–	$2.5 \times 10^{13}$

### Handling/Curing Information    Directions for Use


CAUTION: Use caution if your bond line is thicker than 1 mm as an exothermic reaction may occur during cure with production of intense heat and smoke. The likelihood of this happening depends on your joint design, the mass of material cured, and the ability for heat to be dissipated by the substrates.

1. Warm products to room temperature before opening containers to restore proper application consistency and to prevent moisture condensation on adhesive surface. Containers may be stored at room temperature for 1-2 days to thaw. Do not warm at temperatures above 80°F (27°C).
2. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation directly depends on the substrates, the required bond strength, environmental aging resistance, and requirements determined by the user in light of the user's particular purpose and method of application. For specific surface preparations on common substrates, see the section on surface preparation.
3. Use gloves to minimize skin contact and do not use solvents for cleaning hands.
4. For maximum bond strength, apply product evenly to both surfaces to be joined.
5. Join the adhesive coated surfaces and heat cure using the following bondline temperature and time for the specific product being used.

Any of the following cure cycles will result in a full cure.

3M™ Scotch-Weld™ Adhesive 2214 Regular

3M™ Scotch-Weld™ Adhesive 2214 Hi-Temp



# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

3M™ Scotch-Weld™ Adhesive 2214 Hi-Dense	40 min @ 250°F (121°C)
3M™ Scotch-Weld™ Adhesive 2214 Non-Metallic Filled (177°C)	5 min @ 350°F
3M™ Scotch-Weld™ Adhesive 2214 Hi-Temp (121°C)	60 min @ 250°F
New Formula	15 min @ 300°F (149°C)

6. Keep parts from moving during cure as contact pressure is necessary.
7. Cleanup can be accomplished with solvent such as 3M™ Scotch-Grip™ Solvent No. 3 or Methyl Ethyl Ketone.\*

\*Note: Prior to use of these solvents, extinguish or eliminate any ignition sources and read and follow supplier's environmental, health, and safety recommendations listed on the MSDS and product label.

---

### Surface Preparation

The following cleaning methods are suggested for common surfaces:

#### Steel:

1. Wipe free of dust with oil-free solvent such as Methyl Ethyl Ketone.\*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.

#### Aluminum:

1. Vapor Degrease – Perchloroethylene\* condensing vapors for 5-10 minutes.
2. Alkaline Degrease – Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (87°C ± 5°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
3. Acid (FPL) Etch – Place panels in their following solution for 10 minutes at 150°F ± 5°F (66°C ± 2°C).

Sodium Dichromate	4.1-4.9 oz./gallon
Sulfuric Acid, 66°Be	38.5-41.5 oz./gallon
2024-T3 aluminum (dissolved)	0.2 oz./gallon minimum

Tap water as needed to balance
4. Rinse – Rinse panels in clear running tap water.
5. Dry – Air dry 15 minutes; force dry 10 minutes at 150°F ± 10°F (66°C ± 5°C).
6. If primer is to be used, it should be applied within 4 hours after surface preparation.

#### Plastics:

1. Solvent wipe with Isopropyl Alcohol.\*
2. Abrade using clean fine grit abrasives.
3. Solvent wipe with Isopropyl Alcohol.\*

#### Rubbers:

1. Solvent wipe with Methyl Ethyl Ketone.\*
2. Abrade using clean fine grit abrasives.
3. Solvent wipe with Methyl Ethyl Ketone.\*

#### Glass:

1. Solvent wipe with acetone or Methyl Ethyl Ketone.\*

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

**Note:** For glass applications which will be subjected to high moisture/humidity conditions, 3M™ Scotch-Weld™ Primer EC-3901 should be used to prime the glass.

**\*Note:** Prior to use of these solvents, extinguish or eliminate any ignition sources and read and follow supplier's environmental, health, and safety recommendations listed on the MSDS and product label.

---

### Application/Equipment Information

These products may be applied by spatula, trowel, or flow equipment.

Dispensing equipment is available for intermittent or production line use. These systems are ideal because of their variable shot size and flow rate characteristics and are adaptable to most applications. For more information, contact your local 3M sales representative.

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

### Equipment Suggestions

**Note:** Minimum pumping temperature is 65°F (18°C) for all products.

#### 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Regular Production Extrusion Equipment

Pump	Ram	Hose	Flow Gun
Ratio 55:1 with a chopping check valve and priming piston, 8 in. air motor. 3.7 cu. in./cycle	Pneumatic type capacity-12 psi on material surface	Super high pressure with standard lining	High pressure type

**Output based on 1/4" tip flow gun (material temperature 65°F [18°C])  
(minimum pumping temperature is 65°F [18°C])**

Hose Assembly	Material Pressure (psi)	(Output lbs./min.)
Length-20', I.D.-1/2"	4800*	.36
Length-20', I.D.-3/4"	4800*	1.0

#### 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Non-Metallic Filled Production Extrusion Equipment

Pump	Ram	Hose	Flow Gun
Ratio 38:1 with a chopping check valve and priming piston	Pneumatic type capacity-10 psi on material surface	Super high pressure with standard lining	High pressure type

**Output based on 3/8" tip flow gun-8" diameter air motor  
(minimum pumping temperature is 65°F [18°C])**

Hose Assembly	Material Pressure (psi)	(Output lbs./min.)
Length-10', I.D.-3/4"	3000	2.3
Length-20', I.D.-3/4"	3000	1.6
Length-20', I.D.-3/4" +10, I.D.-1/2"	3000	1.2
Length-20', I.D.-1/2"	3000	.84

#### 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Hi-Temp Production Extrusion Equipment

Pump	Ram	Hose	Flow Gun
Ratio 40:1 with a chopping check valve and priming piston, 6 in. air motor. 2 cu. in./cycle	Pneumatic type capacity-12 psi on material surface	Super high pressure with standard lining	High pressure type

**Output based on 1/4" tip flow gun (material temperature 65°F [18°C])**

Hose Assembly	Material Pressure (psi)	(Output lbs./min.)
Length-20', I.D.-1/2"	2400	.4
Length-20', I.D.-3/4"	2400	1.1

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

**Equipment Suggestions**    **Note:** Minimum pumping temperature is 65°F (18°C) for all products.

(continued)

### 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Hi-Dense Production Extrusion Equipment

Pump	Ram	Hose	Flow Gun
Ratio 55:1 with a chopping check valve and priming piston, 8 in. air motor. 3.7 cu. in./cycle	Pneumatic type capacity-12 psi on material surface	Super high pressure with standard lining	High pressure type

**Output based on 1/4" tip flow gun (material temperature 65°F [18°C])  
(minimum pumping temperature is 65°F [18°C])**

Hose Assembly	Material Pressure (psi)	(Output lbs./min.)
Length-20', I.D.-1/2"	4500*	.45
Length-20', I.D.-3/4"	4500*	.9

### 3M™ Scotch-Weld™ Epoxy Adhesive 2214 Hi-Temp New Formula Production Extrusion Equipment

Pump	Ram	Hose	Flow Gun
Ratio 55:1 with a chopping check valve and priming piston, 8 in. air motor. 3.7 cu. in./cycle	Pneumatic type capacity-12 psi on material surface	Super high pressure with standard lining	High pressure type

**Output based on 1/4" tip flow gun (material temperature 65°F [18°C])  
(minimum pumping temperature is 65°F [18°C])**

Hose Assembly	Material Pressure (psi)	(Output lbs./min.)
Length-20', I.D.-1/2"	4800*	.36
Length-20', I.D.-3/4"	4800*	1.0

\*These pressures will require a special consideration during hose selection. They are actual working pressures.

### Typical Adhesive Performance Characteristics

**Note:** All of the following data was developed using a cure cycle of 40 minutes @ 250°F (121°C) under 25 psi pressure except Scotch-Weld adhesive 2214 Hi-Temp New Formula which was 60 minutes at 250°F (121°C).

#### A. Aluminum Overlap Shear

Overlap shear strength was measured on FPL etched 1" wide by 1/2" overlap specimens. The bonds were made from 2 panels of 4" x 7" x .063", 2024 T3 clad aluminum bonded together and cut into 1" wide specimens. The separation rate of the testing jaws was .1"/minute. Tests similar to ASTM D-1002. (All data in psi).

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Test Temperature	3M™ Scotch-Weld™ Epoxy Adhesive 2214				
	Regular	Hi-Dense	Hi-Temp	Hi-Temp New Formula	Non-Metallic Filled
-67°F (-53°C)	3000	3000	2000	2800	3000
75°F (24°C)	4500	4500	2000	2800	4000
180°F (82°C)	4500	4500	3000	2800	4500
250°F (121°C)	1500	1700	2500	2500	1500
300°F (149°C)	600	600	2500	2000	600



**3M™ Scotch-Weld™  
Epoxy Adhesives**

350°F (177°C)	400	400	900	1200	400
---------------	-----	-----	-----	------	-----

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

### Typical Adhesive Performance Characteristics (*continued*)

#### B. Aluminum T-Peel

T-Peel bonds were measured on 1" wide specimens cut from two FPL etched 8" x 8" x .032" 2024 T3 clad aluminum panels bonded together. The separation rate of the testing jaws was 20"/minute. Tests similar to ASTM D-1876. (All data in lbs./in. of width.)

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Test Temperature	3M™ Scotch-Weld™ Epoxy Adhesive 2214				
	Regular	Hi-Dense	Hi-Temp	Hi-Temp New Formula	Non-Metallic Filled
75°F (24°C)	5	5	2	2	7

#### C. Steel Overlap Shear

Overlap shear strength was measured on 1" wide by 1/2" overlap specimens. These bonds were made on 1" x 4" x .035" thick cold rolled steel which was MEK solvent wiped prior to bonding. The separation rate of the testing jaws was .1"/min. Tests similar to ASTM D-1002. (All data in psi.)

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Test Temperature	3M™ Scotch-Weld™ Epoxy Adhesive 2214				
	Regular	Hi-Dense	Hi-Temp	Hi-Temp New Formula	Non-Metallic Filled
-67°F (-53°C)	3000	3000	1650	2000	3000
75°F (24°C)	2500	2500	2400	2500	2200
180°F (82°C)	2000	2000	2000	2000	2000
250°F (121°C)	800	800	2000	2000	400
300°F (149°C)	200	200	2000	2000	200
350°F (177°C)	100	100	500	700	100

#### D. Steel T-Peel

T-Peel bonds were measured on two 1" wide x 8" long specimens bonded together. These bonds were made on MEK wiped .035" steel. After bonding they were then pulled apart in 180° Peel at a jaw separation rate of 20"/minute rate. Tests similar to ASTM D-1876. (All data in lbs./in. of width.)

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Test Temperature	3M™ Scotch-Weld™ Epoxy Adhesive 2214				
	Regular	Hi-Dense	Hi-Temp	Hi-Temp New Formula	Non-Metallic Filled
75°F (24°C)	50	50	5	5	12

# 3M™ Scotch-Weld™

## Epoxy Adhesives

2214 Regular • 2214 Hi-Dense • 2214 Hi-Temp • 2214 Hi-Temp New Formula • 2214 Non-Metallic Filled

**Environmental Resistance**      **Note: The following data is overlap shear after aging for 365 days in the specified environment. Tests were run on FPL etched aluminum and solvent degreased, sandblasted .035" thick cold rolled steel. Bonds and tests similar to ASTM D-1002. (All data in psi.)**

	3M™ Scotch-Weld™ Epoxy Adhesive 2214			
	Regular	Hi-Dense	Hi-Temp	
	Aluminum	Steel	Aluminum	Steel
Tap Water @ 75°F (24°C)	4630	1620	3060	1580
100% relative humidity @ 120°F (49°C)	1900	1910	3120	2090
Ethyl Gasoline @ 75°F (24°C)	4690	2310	2620	1870

**Storage**      Store products at 40°F (4°C) or below for maximum storage life. Higher temperatures reduce normal storage life. Rotate stock on a “first-in-first-out” basis.  
  
CAUTION: Products are heat sensitive. Storage above 130°F (54°C) may cause an exothermic reaction resulting in evolution of excessive heat, noxious fumes, and possibly fire.

**Shelf Life**      All of these products have a shelf life of 12 months from the date of manufacture when stored in their unopened containers @ 40°F (4°C) or below; or 18 months @ 0°F (-20°C) or below.”

**Precautionary Information**      Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

**Technical Information**      The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use**      Many factors beyond 3M’s control and uniquely within user’s knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer’s application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer**      Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M’s option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability**      Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

ISO 9001:2008



### Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550 • 877-369-2923 (Fax)  
[www.3M.com/structuraladhesives](http://www.3M.com/structuraladhesives)

3M and Scotch-Weld are trademarks of 3M Company.  
©3M 2010