


# High Voltage MLC Chips FLEXITERM®



## For 600V to 3000V Application



High value, low leakage and small size are difficult parameters to obtain in capacitors for high voltage systems. AVX special high voltage MLC chips capacitors meet these performance characteristics and are designed for applications such as snubbers in high frequency power converters, resonators in SMPS, and high voltage coupling/DC blocking. These high voltage chip designs exhibit low ESRs at high frequencies.


To make high voltage chips, larger physical sizes than are normally encountered are necessary. These larger sizes require that special precautions be taken in applying these chips in surface mount assemblies. In response to this, and to follow from the success of the FLEXITERM® range of low voltage parts, AVX is delighted to offer a FLEXITERM® high voltage range of capacitors, FLEXITERM®.

The FLEXITERM® layer is designed to enhance the mechanical flexure and temperature cycling performance of a standard ceramic capacitor, giving customers a solution where board flexure or temperature cycle damage are concerns.

### HOW TO ORDER

<b>1808</b>	<b>A</b>	<b>C</b>	<b>272</b>	<b>K</b>	<b>A</b>	<b>Z</b>	<b>1</b>	<b>A</b>
<b>AVX Style</b>	<b>Voltage</b>	<b>Temperature Coefficient</b>	<b>Capacitance Code</b>	<b>Capacitance Tolerance</b>	<b>Test Level</b>	<b>Termination*</b>	<b>Packaging</b>	<b>Special Code</b>
0805	600V/630V = C 1000V = A	X7R = C	(2 significant digits + no. of zeros)	X7R:K = ±10% M = ±20% Z = +80%, -20%	A = Standard	Z = FLEXITERM® 100% Tin (RoHS Compliant)	1 = 7" Reel 3 = 13" Reel 9 = Bulk	A = Standard
1206	1500V = S		Examples: 10 pF = 100 100 pF = 101 1,000 pF = 102 22,000 pF = 223 220,000 pF = 224 1 μF = 105			X = FLEXITERM® 5% min. Pb		
1210	2000V = G							
1808	2500V = W							
1812	3000V = H							
1825								
2220								
2225								

Notes: Capacitors with X7R dielectrics are not intended for applications across AC supply mains or AC line filtering with polarity reversal. Contact plant for recommendations. Contact factory for availability of Termination and Tolerance options for Specific Part Numbers.



### DIMENSIONS

SIZE	0805	1206	1210*	1808*	1812*	1825*	2220*	2225*	millimeters (inches)
(L) Length	$2.01 \pm 0.20$ ( $0.079 \pm 0.008$ )	$3.20 \pm 0.20$ ( $0.126 \pm 0.008$ )	$3.20 \pm 0.20$ ( $0.126 \pm 0.008$ )	$4.57 \pm 0.25$ ( $0.180 \pm 0.010$ )	$4.50 \pm 0.30$ ( $0.177 \pm 0.012$ )	$4.50 \pm 0.30$ ( $0.177 \pm 0.012$ )	$5.7 \pm 0.40$ ( $0.224 \pm 0.016$ )	$5.72 \pm 0.25$ ( $0.225 \pm 0.010$ )	
(W) Width	$1.25 \pm 0.20$ ( $0.049 \pm 0.008$ )	$1.60 \pm 0.20$ ( $0.063 \pm 0.008$ )	$2.50 \pm 0.20$ ( $0.098 \pm 0.008$ )	$2.03 \pm 0.25$ ( $0.080 \pm 0.010$ )	$3.20 \pm 0.20$ ( $0.126 \pm 0.008$ )	$6.40 \pm 0.30$ ( $0.252 \pm 0.012$ )	$5.0 \pm 0.40$ ( $0.197 \pm 0.016$ )	$6.35 \pm 0.25$ ( $0.250 \pm 0.010$ )	
(T) Thickness Max.	1.30 (0.051)	1.52 (0.060)	1.70 (0.067)	2.03 (0.080)	2.54 (0.100)	2.54 (0.100)	3.30 (0.130)	2.54 (0.100)	
(t) terminal min. max.	$0.50 \pm 0.25$ ( $0.020 \pm 0.010$ )	0.25 (0.010) 0.75 (0.030)	0.25 (0.010) 0.75 (0.030)	0.25 (0.010) 1.02 (0.040)	0.25 (0.010) 1.02 (0.040)	0.25 (0.010) 1.02 (0.040)	0.25 (0.010) 1.02 (0.040)	0.25 (0.010) 1.02 (0.040)	

\*Reflow Soldering Only

# High Voltage MLC Chips FLEXITERM®



For 600V to 3000V Applications

## X7R Dielectric

### Performance Characteristics

Capacitance Range	390 pF to 0.33 µF (25°C, 1.0 ±0.2 Vrms at 1kHz)
Capacitance Tolerances	±10%; ±20%; +80%, -20%
Dissipation Factor	2.5% max. (+25°C, 1.0 ±0.2 Vrms, 1kHz)
Operating Temperature Range	-55°C to +125°C
Temperature Characteristic	±15% (0 VDC)
Voltage Ratings	600, 630, 1000, 1500, 2000, 2500 & 3000 VDC (+125°C)
Insulation Resistance (+25°C, at 500 VDC)	100K MΩ min. or 1000 MΩ - µF min., whichever is less
Insulation Resistance (+125°C, at 500 VDC)	10K MΩ min. or 100 MΩ - µF min., whichever is less
Dielectric Strength	Minimum 120% rated voltage for 5 seconds at 50 mA max. current

## HIGH VOLTAGE X7R MAXIMUM CAPACITANCE VALUES

VOLTAGE	0805	1206	1210	1808	1812	1825	2220	2225
600/630 min.	1800pF	8200 pF	0.018 µF	0.022 µF	0.039 µF	0.100 µF	0.100 µF	0.100 µF
600/630 max.	6800pF 0.022 µF	0.022 µF	0.056 µF	0.068 µF	0.120 µF	0.270 µF	0.270 µF	0.330 µF
1000 min.	390pF	3300 pF	8200 pF	8200 pF	0.015 µF	0.047 µF	0.047 µF	0.047 µF
1000 max.	1500pF	6800 pF	0.015 µF	0.018 µF	0.039 µF	0.100 µF	0.120 µF	0.150 µF
1500 min.	—	1800 pF	4700 pF	3900 pF	6800 pF	0.022 µF	0.022 µF	0.022 µF
1500 max.	—	2700 pF	6800 pF	6800 pF	0.015 µF	0.056 µF	0.056 µF	0.068 µF
2000 min.	—	820 pF	1500 pF	2200 pF	4700 pF	0.015 µF	0.015 µF	0.015 µF
2000 max.	—	1500 pF	3900 pF	3300 pF	8200 pF	0.027 µF	0.027 µF	0.033 µF
2500 min.	—	—	—	1500 pF	3300 pF	8200 pF	0.010 µF	0.012 µF
2500 max.	—	—	—	2200 pF	5600 pF	0.015 µF	0.018 µF	0.022 µF
3000 min.	—	—	—	1000 pF	1800 pF	5600 pF	6800 pF	8200 pF
3000 max.	—	—	—	1800 pF	4700 pF	0.012 µF	0.012 µF	0.015 µF