

Electrical Properties:

Property	Test Method
RTG Resistance:	ESD S4.1
RTT Resistance:	ESD S4.1

<u>Value</u> 10⁷ - 10⁸ Ohms 10⁷ - 10⁸ Ohms

Electrical Properties obtained by testing to industrial standards by an independent testing laboratory @ 100 Volts and 50% relative humidity unless otherwise specified. Complete text of the test report is available upon request.

Disclaimer:

All statements, technical data, and recommendations contained herein are based upon tests we believe to be reliable. However, the accuracy or completeness thereof is not guaranteed. The proper and correct applications of products and data is the responsibility of the user. Statements or recommendations not contained herein shall have no force or effect unless embodied in a written agreement signed by authorized officers of Desco Industries, Inc.

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.

Specifications:

Construction:	Homogeneous extruded	
	thermoplastic vinyl	•
Thickness:	0.100" (2.5mm) and 0.060" (1.5mm),	
	nominal ±10%	
Texture:*	One side smooth, one side embossed	
Colors:*	Blue, Beige	
Hardness:	80 shore A (ASTM D-2240)	
Wear Resistance:	Negligible weight loss (750 cycles, Tabe	r CS-17
	Method)	
*Color, texture, and	gauge may vary between lots and mills	

<u>Grounding</u>: This material must be properly grounded for optimum electrial performance. Ask for Technical Bulletin TB-2000 for mat grounding instructions.

<u>Cleaning:</u> For optimum electrical performance, surface must be cleaned regularly using an ESD mat cleaner. We suggest using our Reztore[™] Surface & Mat Cleaner Item #10435 or Static-Wipes Item #10600. Do not use cleaners with silicone. Silicone buildup will create an insulative film on the surface.

See reverse side for available mat and roll sizes

Blue, Beige

Description:

Statfree B[™] meets the minimum recommended worksurface requirement of ANSI/ESD S20.20 of <10E9 ohms. This extruded homogeneous vinyl dissipative material can be used with either side up. One side has a smooth surface which is easy-to-clean and maintain, and the other has a non-glare finish which makes it easier to identify small parts. Statfree B[™] is easy to cut to configure to fit your requirements. The material is dimensionally stable with minimum shrinkage or curling.

Statfree B[™] has excellent color stability, minimizing discoloration. The 0.100" thick is a better value, providing a longer life and is ideal for general purpose worksurface matting. The thinner 0.060" material is the economical choice, and is ideal for use on cafeteria-style trays.

Statfree B[™] is manufactured without any ozone depleting substances, and in accordance with the Montreal Protocol.

Tolerances:

Width +/- .250" Length +/- .250" every 1 linear foot of running material.

Limited Lifetime Warranty:

Desco warrants for one year that Statfree[®] matting products will be free of defects in materials and workmanship and will guarantee dissipative/conductive mat properties for the life of the mat. Damage to matting caused by misuse of any kind, including using inappropriate cleaners is not covered by Desco Limited Warranty.



Note: Since it does not have a conductive layer, Statfree B[™] is not suitable for use with continuous monitors.

STATFREE B[™] MATERIAL, VINYL, DISSIPATIVE, HOMOGENEOUS, .100" & .060"

DESCO	DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: www.desco.com PHONE (909) 627-8178 FAX (909) 627-7449	MATERIAL STATFREE B™	DATE : 4/05
	DESCO EAST: 90 HUDSON RD, CANTON, MA 02021-1407 PHONE (781) 821-8370 FAX (781) 575-0172	DRAWING PM-78	



© 2005 DESCO INDUSTRIES INC. Employee Owned