Fair-Rite Products Corp.

Your Signal Solution[®]

Multi- Aperture cores (2843001502)



Part Number: 2843001502

43 MULTI- APERTURE CORE

Explanation of Part Numbers: – Digits 1 & 2 = Product Class – Digits 3 & 4 = Material Grade

-Last digit 2 = Burnished

Multi- aperture cores are used in suppression applications and in balun (balance- unbalance) and other broadband transformers. They are also employed in airbag designs to prevent accidental activation.

All multi- aperture cores are supplied burnished.

Our "Multi- Aperture Core Kit" (part number 0199000036) is available for prototype evaluation.

For any multi- aperture requirement not listed here, feel free to contact our customer service group for availability and pricing.

Catalog Drawing 3D Model

Weight: 1.7 (g)

Dim	mm	mm tol	nominal inch	inch misc.		
А	13.3	±0.60	0.524		0	1 1111
В	6.6	±0.25	0.26			E 77777 A
С	7.5	±0.35	0.295		-(0)	· · · · · · · ·
Е	5.7	±0.25	0.224			
Н	3.8	±0.25	0.15			B
-			*		- C -	

Figure 1


Chart Legend		
+ Test frequency		
· Test nequency		

Typical Impedance (Ω)					
25 MHz	70				
100 MHz^+	106				

Multi- aperture cores in 73 and 43 materials are controlled for impedance only. The 61 NiZn material is controlled for both impedance and A_L value. The high frequency 67 material is controlled for A_L value. Minimum impedance values are specified for the + marked frequencies. The minimum impedance is typically the listed impedance less 20%.

Multi- aperture cores in 73 and 43 material are measured for impedance on the E4990A Impedance Analyzer. The 61 and 67 multi- aperture cores are tested on the E4991A / HP4291B Impedance Analyzer. All impedance measurements are performed with a single turn to both holes, using the shortest practical wire length.

The 61 and 67 material multi- hole beads are tested for A_L value. The test frequency is 10 kHz at < 10 gauss. The test winding is five turns wound through both holes.



CSV Download

	Fai	r- Rite Products Co	orp.		One Commercia	l Rov	v, Wallkill, New York 1258	39-02	88
888-324-7748		845-895-2055		Fax	845-895-2629		ferrites@fair- rite.com		www.fair- rite.com