No.


1. Scope

This specification covers basic requirements for the structure and optical performances of GHTT-4001.

2. Structure

Table 1				GHTT-4001		
Item		Specification				
		Unit	Min.	Тур.	Max.	
Optical Fiber	Core Material	_	Polymethyl-Methacrylate Resin			
	Cladding Material	_	Fluorinated Polymer			
	Core Refractive Index	_	1.49			
	Refractive Index Profile	_	Step Index			
	Numerical Aperture	_	0.5			
	Core Diameter	μm	920	980	1,040	
	Cladding Diameter	μm	940	1,000	1,060	
Jacket	Material	_	Polyethylene			
	Color	_	Black			
	Dimention	mm	2.13	2.20	2.27	
Number of cords		_	1			
Strength Member	Material	_	Aramid Fiber			
Sheath	Material	_	Poly-Vinyl-Chloride			
	Color	_	Gray			
	Diameter	mm	4.8	5.0	5.2	
Approximate Weight		g/m	27			
Indication on the Jacket			●●● 🙏 ESKA PREMIER ●●●:Pink			

## Sectional View



No.

## 3. Performances

Table 2 GHTT-4001 Acceptance Criterion Specification Item and/or [ Test Condition ] Unit Min. Тур. Max. Storage No Physical Deterioration  $^{\circ}$ C -40 +85 Temperature [in a Dry Atmosphere] No Deterioration Maximum  $^{\circ}$ C -40 +85 in Optical Properties\* Rating Operation [in a Dry Atmosphere] Temperature No Deterioration  $^{\circ}$ C +75 in Optical Properties\*\* [under 95%RH condition] [25°C 50%RH] dB/km 170 Transmission Loss Optical [650nm **Properties** Collimated Light ] [ Operation Temperature ] dB/km 190 Loss Increment ≦0.5dB Minimum mm 40 Bend Radius [ A Quarter Bend ] Loss Increment ≦1dB Repeated Bending [ in Conformity to the Times 5,000 Endurance JIS C 6861 ]\*\*\* Mechanical [ in Conformity Allowable Tension Ν 245 Characteristics to the JIS C 6861 ] Loss Increment ≦1dB Twisting Endurance [ Sample Length: 1m Times 5 Tensile Force: 4.9N] Loss Increment ≦1dB Impact Endurance [ in Conformity to the N·m

All tests are carried out under temperature of 25°C unless otherwise specified.

JIS C 6861 ]

The specifications is subject to change without notice.

The information contained herein is presented as guide for the product selection.

Please contact our business department for the issue of an official specification sheet.

<sup>\*</sup> Attenuation change shall be within +/- 10% after 1,000 hours.

<sup>\*\*</sup> Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

<sup>\*\*\*</sup> Bend Angle +/-90°, Bend Radius 15mm, Tension 500g